



# Makrolon® 2407

Covestro - Polycarbonates - Polycarbonate

Tuesday, April 9, 2019

## General Information

### Product Description

MVR (300°C/1.2 kg) 19 cm<sup>3</sup>/10 min; general purpose; low viscosity; UV stabilized; easy release; injection molding - melt temperature 280 - 320°C; available in transparent, translucent and opaque colors

### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• General Purpose	• Good Mold Release	• Low Viscosity
Uses	• General Purpose		
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FORD WSK-M4D761-A2 • FORD WSK-M4D761-A2 Color: Transparent • GM GMP.PC.005 • GM GMP.PC.007	• GM GMW15702-455303 PC • GM GMW16728P-PC-T4 • GM GMW16728P-PC-T4 Color: 550115 Clear • GM GMW16728P-PC-T4 Color: 901510 Colored	• GM QK 005941 LR Color: 550115 Colorless • SAE J576
Appearance	• Clear/Transparent • Colors Available	• Opaque • Translucent	
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density (73°F (23°C))	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>	ISO 1183
Apparent (Bulk) Density <sup>2</sup>	0.66 g/cm <sup>3</sup>	0.66 g/cm <sup>3</sup>	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20 g/10 min	20 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	19 cm <sup>3</sup> /10min	19 cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			
Across Flow	0.50 to 0.70 %	0.50 to 0.70 %	ISO 2577
Flow	0.50 to 0.70 %	0.50 to 0.70 %	ISO 2577
Across Flow : 536°F (280°C), 0.0787 in (2.00 mm) <sup>3</sup>	0.70 %	0.70 %	ISO 294-4
Flow : 0.0787 in (2.00 mm) <sup>3</sup>	0.65 %	0.65 %	ISO 294-4
Water Absorption			
Saturation, 73°F (23°C)	0.30 %	0.30 %	ISO 62
Equilibrium, 73°F (23°C), 50% RH	0.12 %	0.12 %	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	348000 psi	2400 MPa	ISO 527-2/1
Tensile Stress			
Yield, 73°F (23°C)	9570 psi	66.0 MPa	ISO 527-2/50
Break, 73°F (23°C)	9430 psi	65.0 MPa	

Copyright ©, 2019 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Makrolon® 2407

## Covestro - Polycarbonates - Polycarbonate

Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strain			ISO 527-2/50
Yield, 73°F (23°C)	6.0 %	6.0 %	
Break, 73°F (23°C)	120 %	120 %	
Nominal Tensile Strain at Break			ISO 527-2/50
73°F (23°C)	> 50 %	> 50 %	
Tensile Creep Modulus			ISO 899-1
1 hr	319000 psi	2200 MPa	
1000 hr	276000 psi	1900 MPa	
Flexural Modulus <sup>4</sup> (73°F (23°C))	341000 psi	2350 MPa	ISO 178
Flexural Stress <sup>4</sup>			ISO 178
3.5% Strain, 73°F (23°C)	10700 psi	74.0 MPa	
73°F (23°C)	14200 psi	98.0 MPa	
Flexural Strain at Flexural Strength <sup>5</sup>			ISO 178
73°F (23°C)	7.0 %	7.0 %	
Films	Typical Value (English)	Typical Value (SI)	Test Method
Water Vapor Transmission Rate			ISO 15106-1
73°F (23°C), 85% RH, 3.9 mil (100 µm)	0.97 g/100 in <sup>2</sup> /24 hr	15 g/m <sup>2</sup> /24 hr	
Carbon Dioxide Permeability			ISO 2556
73°F (23°C), 1.0 mil (25.4 µm)	18900 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	18900 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Gas Permeation			ISO 2556
Carbon Dioxide : 3.9 mil (100.0 µm)	4800 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	4800 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Nitrogen : 1.0 mil (25.4 µm)	630 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	630 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Nitrogen : 3.9 mil (100.0 µm)	160 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	160 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Oxygen : 1.0 mil (25.4 µm)	3150 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	3150 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Oxygen : 3.9 mil (100.0 µm)	800 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	800 cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength <sup>6</sup>			ISO 179/1eA
-22°F (-30°C), Complete Break	6.7 ft·lb/in <sup>2</sup>	14 kJ/m <sup>2</sup>	
73°F (23°C), Partial Break	31 ft·lb/in <sup>2</sup>	65 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-76°F (-60°C)	No Break	No Break	
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Notched Izod Impact Strength <sup>6</sup>			ISO 180/A
-22°F (-30°C), Complete Break	5.7 ft·lb/in <sup>2</sup>	12 kJ/m <sup>2</sup>	
73°F (23°C), Partial Break	31 ft·lb/in <sup>2</sup>	65 kJ/m <sup>2</sup>	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-22°F (-30°C)	47.9 ft·lb	65.0 J	
73°F (23°C)	40.6 ft·lb	55.0 J	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-22°F (-30°C)	1350 lbf	6000 N	
73°F (23°C)	1150 lbf	5100 N	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Ball Indentation Hardness	16800 psi	116 MPa	ISO 2039-1

Copyright ©, 2019 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Makrolon® 2407

## Covestro - Polycarbonates - Polycarbonate

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	277 °F	136 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	255 °F	124 °C	ISO 75-2/A
Glass Transition Temperature <sup>7</sup>	289 °F	143 °C	ISO 11357-2
Vicat Softening Temperature			
--	289 °F	143 °C	ISO 306/B50
--	293 °F	145 °C	ISO 306/B120
Ball Pressure Test (275°F (135°C))	Pass	Pass	IEC 60695-10-2
CLTE			ISO 11359-2
Flow : 73 to 131°F (23 to 55°C)	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	
Transverse : 73 to 131°F (23 to 55°C)	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	
Thermal Conductivity <sup>8</sup> (73°F (23°C))	1.4 Btu·in/hr/ft <sup>2</sup> /°F	0.20 W/m/K	ISO 8302
RTI Elec (0.06 in (1.5 mm))	257 °F	125 °C	UL 746
RTI Imp (0.06 in (1.5 mm))	239 °F	115 °C	UL 746
RTI Str (0.06 in (1.5 mm))	257 °F	125 °C	UL 746
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F (23°C))	1.0E+16 ohms·cm	1.0E+16 ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
73°F (23°C), 0.0394 in (1.00 mm)	860 V/mil	34 kV/mm	
Relative Permittivity			IEC 60250
73°F (23°C), 100 Hz	3.10	3.10	
73°F (23°C), 1 MHz	3.00	3.00	
Dissipation Factor			IEC 60250
73°F (23°C), 100 Hz	5.0E-4	5.0E-4	
73°F (23°C), 1 MHz	9.0E-3	9.0E-3	
Comparative Tracking Index			IEC 60112
Solution A	250 V	250 V	
Solution B	125 V	125 V	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.11 in (2.7 mm)	HB	HB	
0.030 in (0.75 mm)	V-2	V-2	
Glow Wire Flammability Index			IEC 60695-2-12
0.030 in (0.75 mm)	1560 °F	850 °C	
0.06 in (1.5 mm)	1610 °F	875 °C	
0.12 in (3.0 mm)	1710 °F	930 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.030 in (0.75 mm)	1610 °F	875 °C	
0.04 in (1.0 mm)	1610 °F	875 °C	
0.06 in (1.5 mm)	1610 °F	875 °C	
0.12 in (3.0 mm)	1610 °F	875 °C	
Oxygen Index <sup>9</sup>	27 %	27 %	ISO 4589-2
Application of Flame from Small Burner <sup>10</sup>	K1, F1	K1, F1	DIN 53438-1, -3
Burning Rate <sup>11</sup> (> 39.4 mil (> 1.00 mm))	passed	passed	ISO 3795
Flash Ignition Temperature	896 °F	480 °C	ASTM D1929

Copyright ©, 2019 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Makrolon® 2407

## Covestro - Polycarbonates - Polycarbonate

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Needle Flame Test			IEC 60695-11-5
59.1 mil (1.50 mm) <sup>12</sup>	1.0 min	1.0 min	
59.1 mil (1.50 mm) <sup>13</sup>	0.1 min	0.1 min	
78.7 mil (2.00 mm) <sup>13</sup>	0.1 min	0.1 min	
78.7 mil (2.00 mm) <sup>12</sup>	2.0 min	2.0 min	
0.12 in (3.00 mm) <sup>12</sup>	2.0 min	2.0 min	
0.12 in (3.00 mm) <sup>13</sup>	0.2 min	0.2 min	
Self Ignition Temperature	1022 °F	550 °C	ASTM D1929
Optical	Typical Value (English)	Typical Value (SI)	Test Method
Refractive Index <sup>14</sup>	1.584	1.584	ISO 489
Transmittance			ISO 13468-2
39.4 mil (1000 µm)	89.0 %	89.0 %	
78.7 mil (2000 µm)	89.0 %	89.0 %	
118 mil (3000 µm)	88.0 %	88.0 %	
157 mil (4000 µm)	87.0 %	87.0 %	
Haze (118 mil (3000 µm))	< 0.800 %	< 0.800 %	ISO 14782
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Electrolytical Corrosion (73°F (23°C))	A1	A1	IEC 60426
ISO Shortname	7391-PC,MLR,(,)- 18-9	7391-PC,MLR,(,)- 18-9	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature - Dry Air Dryer	248 °F	120 °C
Drying Time - Dry Air Dryer	4.0 hr	4.0 hr
Suggested Max Moisture	< 0.020 %	< 0.020 %
Suggested Shot Size	30 to 70 %	30 to 70 %
Rear Temperature	482 to 518 °F	250 to 270 °C
Middle Temperature	518 to 554 °F	270 to 290 °C
Front Temperature	545 to 581 °F	285 to 305 °C
Nozzle Temperature	518 to 581 °F	270 to 305 °C
Processing (Melt) Temp	536 to 608 °F	280 to 320 °C
Mold Temperature	158 to 230 °F	70 to 110 °C
Back Pressure	1450 to 2900 psi	10.0 to 20.0 MPa
Vent Depth	9.8E-4 to 3.0E-3 in	0.025 to 0.075 mm

### Injection Notes

Standard Melt Temperature: 300°C  
 Hold Pressure (% of Injection Pressure): 50 - 75%  
 Peripheral Screw Speed: 0.05 - 0.2 m/s

Copyright ©, 2019 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Makrolon® 2407

## Covestro - Polycarbonates - Polycarbonate

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Pellets

<sup>3</sup> 60x60x2mm, 500 bar

<sup>4</sup> 0.079 in/min (2.0 mm/min)

<sup>5</sup> 2 mm/min

<sup>6</sup> 3 mm

<sup>7</sup> 10°C/min

<sup>8</sup> Across Flow

<sup>9</sup> Procedure A

<sup>10</sup> Method K and F

<sup>11</sup> US-FMVSS

<sup>12</sup> Method F

<sup>13</sup> Method K

<sup>14</sup> Method A